

MACal[®] 9700 PRO

Technical Data Sheet

PRODUCT DESCRIPTION

MACal 9700 PRO is translucent when backlit, and opaque when not illuminated, and is manufactured in such a way so as to guarantee uniform colour reproduction.

The soft films are coated with a long-life durable, highly cohesive acrylic pressure-sensitive adhesive, which is protected with a high quality siliconized kraft paper liner.

CONSTRUCTION

Face material :

80 µm matt translucent polymeric stabilized vinyl film, cadmium-free.

Adhesive :

High quality acrylic solvent based adhesive, very cohesive and extremely durable.

Liner :

Highly stable 135 gsm white kraft paper with blue backprinting.

TYPICAL USES

Decoration and identification of internally illuminated signs made from glass, acrylic, stretched plasticized fabric, etc.

Suitable for outdoor and indoor applications.

DURABILITY

5-7 years

These use-life estimates are based upon accelerated ageing studies and outdoor exposure, under conditions experienced in vertical exposure and in "normal" temperate climates.

Note : Exposure to severe temperatures, ultraviolet light or conditions in southern European countries, as well as in tropical, sub-tropical or desert regions, will cause a more rapid deterioration. This also applies to polluted areas, high altitude and south-facing exposure.

SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity.

PHYSICAL PROPERTIES (Average values)

Thickness (mm) (Film + adhesive) ASTM D-645
0.115

Face Material Data, 23°C DIN 53455

Tensile strength : ≥ 1.10 kN/m

Elongation at break : ≥ 100 %

Adhesive Data, 23°C FTM 1

Peel adhesion 180° on stainless steel (N/25 mm)

- 20 min. residence : > 16

- 1 week residence : > 20

Dimensional stability FTM 14

Shrinkage (48 hours at 70°C) : < 0.2 %

(25 cm x 25 cm, sample mounted on aluminium).

Temperature ranges :

Application : + 10°C to + 40°C

End-use : - 40°C to + 90°C

N.B. : for lower temperatures, please consult us.

Flammability ISO 3795

Sample mounted on aluminium : self-extinguishing.

Solvent and chemical resistance

Resistant to most oils and greases, fuel, aliphatic solvents, weak acids, salts and alkalis.

Important notice

Care should be taken when selecting a substrate for use in illuminated devices with self-adhesive materials. Some substrates, e.g. polycarbonate, can cause problems because of "bubbling".

It is therefore recommended that trials be conducted to establish the compatibility of the MACal 9700 PRO vinyl film with the application surface.

PROCESSING

Computer cutting

Clean, quick, trouble-free cutting with most plotters. Adjustment of the cutting depth is important : if the cut is too deep this could result in the paper splitting and coming away with the adhesive when the vinyl is transferred to Application Tape.

Application

Application of MACal 9700 PRO Series is made easier if MACtransfer 200 Application Tape is used.

IMPORTANT NOTICE

All MACTac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects.

Published information concerning MACTac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACTac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages.

All specifications are subject to change without prior notice.