

# Metallized MACtab FA 103 Century 6

## FACE MATERIAL

**Based on a 80gr/sqm white wood free paper to which a bright metallic film is applied, it gives a smooth high quality gloss finish.**

The vinyl acrylic coating allows good ink receptivity and can be printed by letterpress, flexo, offset and hot stamping process. Maximum temperature of 80°C at the drying station is recommended in order to avoid matification of the coating. Corona treatment before printing can enhance printability.

### Application

**Metallized MACtab are glossy transfer metallized paper designed for all applications (cosmetic, sweets, toiletries) where a metallic finish is required, combined with a hotfoil stamping process.**

Available in bright silver. For applications on very curved surfaces (< 15mm diameter), we recommend our Macflex face stock.

### Technical Characteristics

<b>Thickness</b>	75 ± 6 µ	ISO 534
<b>Weight</b>	76 ± 5 gr/sqm	ISO 536
<b>Tensile strength</b>	min. 66 N/15 mm M.D.	ISO 1924-1
	min. 37 N/15 mm C.D.	

## ADHESIVE

**FA 103** is a permanent acrylic adhesive, emulsion based, specially conceived to be converted and applied on meat. It is suitable for high converting speeds and will achieve optimal dispensing.

**Certification :** Direct contact dry, moist and some fatty foodstuffs (25279 U 07)

### Properties

<b>Quick Tack</b>	min. 8	N/25 mm on glass	FTM 9
<b>Release force</b>	0,11 ± 0,4	N/25 mm at 100 m/min.	FTM 4
<b>Application temperature</b>	min. + 5 °C		
<b>Service temperature</b>	- 15 °C to + 80 °C		

## BACKING

Super calendered glassine backing paper combining high flexibility and consistent caliper for speed and ease of conversion with good translucency for optical scanning. Excellent resistance to die cutting.

### Technical Characteristics

<b>Thickness</b>	55 ± 6 µm	ISO 534
<b>Weight</b>	60 ± 5 gr/m <sup>2</sup>	ISO 536
<b>Tensile strength</b>	Minimum 75 N/15mm	M.D. ISO 1924
<b>Transparency</b>	minimum 46 %	DIN 53147

**Shelf life:** 2 years when stored at 15-25°C, (50 ± 5) % relative humidity, in the original packaging.



MACtac Europe  
Bd Kennedy, Zoning Industriel, Zone B  
B-7060 Soignies Belgium  
Phone : +32 (0) 67 346 211  
Fax : +32 (0) 67 346 339  
[www.mactac-europe.com](http://www.mactac-europe.com)  
e-mail : [mactac.europe@mactac.com](mailto:mactac.europe@mactac.com)



---

*All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of quality and free from manufacturing defects.*

*Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.*

*Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice.*