

MACtab White MR 101 Secury 9

FACE MATERIAL

White wood-free, non-coated writing paper.

MACtab may be printed with fair results by flexo, letterpress, gravure and offset and particularly suitable for applications where better quality printing with a non-coated finish is required.

Application

It is suitable as universal use self-adhesive paper for a wide range of plain and multicolour label applications, such as systems labels, on pack promotions and point of sales labels...

Technical Characteristics

Thickness	71 ± 5 µm	ISO 534
Weight	73 ± 7 gr/sqm	ISO 536
Tensile strength	min. 82 N/15 mm M.D. min. 37 N/15 mm C.D.	ISO 1924-1
Opacity	≥ 82 %	ISO 2471
Smoothness	min 300 sec	Bekk

ADHESIVE

Emulsion acrylic removable adhesive, particularly adapted for high converting speeds. This adhesive is not suitable for application on synthetic materials containing migratory plasticizers. Therefore it is recommended to test the fitness and performance of the product for the intended use.

Certification : Indirect contact foodstuffs (26817 U 08)

Properties

Quick Tack	≥ 3,0	N/25 mm on glass	FTM 9
Adhesion, Peel 20 min.	min. 1,7	N/25 mm on glass	FTM 2
Application temperature	above - 5°C		
Service temperature	- 20°C to + 80°C		

BACKING

Secury 9 : special quality white kraft based siliconized paper.

One side coated, with excellent mechanical properties such as dimensional stability. Very good characteristics for fan folding applications.

Technical Characteristics

Thickness	90 ± 7 µ	ISO 534
Weight	80 ± 6 gr/sqm	ISO 536
Opacity	minimum 85%	ISO 2471

Shelf life: 2 years when stored at 15-25°C, (50 ± 5) % relative humidity, in the original packaging.



MACtac Europe
Bd Kennedy, Zoning Industriel, Zone B
B-7060 Soignies Belgium
Phone : +32 (0) 67 346 211
Fax : +32 (0) 67 346 339
www.mactac-europe.com
e-mail : mactac.europe@mactac.com



All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of quality and free from manufacturing defects.

Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice.