

MACbond B 2170

GENERAL INTRODUCTION


MACbond

- is an assembling system consisting of a thin carrier (paper, non woven, film or others), coated on both sides with a uniform layer of adhesive.
- the adhesives used are pressure-sensitive acrylic polymer or synthetic rubber based formulations.
- is produced in roll or sheet format with a single or double release liner, so that the product chosen best suits the customer's needs.

PRODUCT DESCRIPTION

MACbond B 2170 consists of a 12 μ polyester carrier coated on both sides with an acrylic adhesive. It offers high tack and peel properties with medium shear resistance.

MACbond B 2170 is produced in self-wound format on a honey kraft release liner.



TYPICAL APPLICATION

General purpose : nameplates, electrical fascia panels, automotive fascia panels. White Goods Industry : Gasket and seal mounting, decorative trim bonding.

CHARACTERISTICS

Adhesion with Substrates

Metal / Aluminium	High	Textile/Cotton	High
Glass / Ceramics	High	Rubber/EPDM	Medium
Painted Surface	High	Acrylic/PET	High
Wood/Board/Paper	High	Polystyrene	High
Soft PVC	Medium	PP/PE/PS	High
Rigid PVC	High	Smooth substrate	High
PC/ABS	High	Rough substrate	High

RESISTANCE

Resistant to water, detergents and alcohol. Medium resistance to plasticizers and medium outdoor resistance. Not recommended for use in contact with aliphatic or aromatic hydrocarbons. For further technical advice, please consult with MACtac.

SHELF LIFE

1 year when stored at 15/25°C and 50% relative humidity.

**ADHESIVE
DATA**

	TYPICAL VALUES (*)	TEST METHOD
Quick Tack (N/25mm) on stainless steel	30	FTM 9
Peel 180°- (N/25mm) on stainless steel		
- after 20 minutes	27	FTM 1
- after 24 hours	27	FTM 1
Shear on stainless steel 1kg-25 mm x 25mm (hours)	400	FTM 8

**CARRIER
DATA**

	TYPICAL VALUES (*)	TEST METHOD
Thickness (μ)	12	ISO 534
Tensile (N/15mm) (min.)	MD 25 CD 27	DIN 53455
Elongation (%) (max.)	MD 180 CD 180	DIN 53455

**TEMPERATURE
RESISTANCE**

Minimum application temperature	+ 8°C	
End-use temperature range	-40°C to +130°C	
Short term resistance	+ 190°C	S.A.F.T. 500grs

For temperatures outside those quoted above, please consult with MACtac.

**RELEASE
LINER

THICKNESS
(Carrier+Adhesive)**

Silicone paper yellow of 90 gr/sqm		ISO 536
90 μ		ISO 534

(*) Values given are typical and are not necessarily for use in specifications.

IMPORTANT NOTICE

All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning MACtac products are based upon research which the Company believes to be reliable but such information do not constitute a warranty. Because of the variety of possible uses for MACtac products and the continuing development of new uses, the purchaser should carefully consider the fitness and performance of the product for each intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product or for incidental or consequential damages. All specifications are subject to change without prior notice.

