


MACmount M 1770

MACmount

- is a pressure-sensitive fastening system consisting of a variety of cross linked, closed-cell, polyethylene foams in various thicknesses, densities and colours, and coated both sides with specifically formulated pressure-sensitive adhesives.

MACmount M 1770 consists of a 3.2 mm white, cross-linked, closed-cell, polyethylene foam coated on both sides with a rubber based adhesive. It offers very high peel and shear properties.

MACmount M 1770 is produced in self wound format on a calendered paper liner.



For use when the application requires a 3,2 mm / medium density foam

Adhesion with Substrates

Metal / Aluminium	High	Textile/Cotton	High
Glass / Ceramics	High	Rubber/EPDM	High
Painted Surface	High	Acrylic/PET	High
Wood/Board/Paper	High	Polystyrene	High
Soft PVC	Low	PP/PE/PS	High
Rigid PVC	High	Smooth substrate	High
PC/ABS	High	Rough substrate	High

Resistant to water, detergents, alcohol. Not recommended for use in contact with aliphatic or aromatic hydrocarbons.

2 years when stored at 15 to 25°C and ± 50 % relative humidity.

GENERAL INTRODUCTION

PRODUCT DESCRIPTION

TYPICAL APPLICATION

CHARACTERISTICS

RESISTANCE

SHELF LIFE

**ADHESIVE
DATA**

	TYPICAL VALUES (*)	TEST METHOD
Peel 180°- 20 min (N/25mm) on stainless steel	> 17 (**)	FTM 1
Peel (N/25mm) 23°C	> 17 (**)	AFERA 4001
70°C	> 2 (**)	
Shear on stainless steel (hours) 1kg-25 mm x 25mm	> 1000	FTM 8
AFERA 4012 shear results are available on request		
(**) Foam cleavage		

**CARRIER
DATA**

	TYPICAL VALUES (*)	TEST METHOD
Tensile (N/15mm) (min.)	MD 34.5 CD 24	DIN 53455
Elongation (%) (max.)	MD 250 CD 150	DIN 53455
Density	Medium	

**TEMPERATURE
RESISTANCE**

Minimum application temperature	+ 10°C
End-use temperature range	- 40°C to +60°C

For temperatures outside those quoted above, please consult with MACtac.

**RELEASE
LINER
THICKNESS
(Foam + adhesive)**

Silicone paper white of 90 gr/sqm	ISO 536
3,3 mm	ISO 534

(*) Values given are typical and are not necessarily for use in specifications.

IMPORTANT NOTICE

All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning MACtac products are based upon research which the Company believes to be reliable but such information do not constitute a warranty. Because of the variety of possible uses for MACtac products and the continuing development of new uses, the purchaser should carefully consider the fitness and performance of the product for each intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product or for incidental or consequential damages. All specifications are subject to change without prior notice.

